



2205-2D

For welding steels such as					
Outokumpu	EN	ASTM	BS	NF	SS
2205	1.4462	S32205	318S13	Z3 CND 22-05 Az	2377

Standard designations

EN 1600 E 22 9 3 N L R
 AWS A5.4 E2209-17

Characteristics

AVESTA 2205-2D is a high recovery electrode designed for welding duplex steels such as 2205. For light to moderate thickness material, welding should be carried out as for ordinary austenitic stainless steel. However, the somewhat lower penetration and fluidity of the weld should be considered. Very high quench rates and excessive times at red heat or above should be avoided to prevent excessive ferrite or formation of intermetallic phases.

Welding data

DC+ or AC	Diam. mm	Current, A
	4.0	110 – 170
	5.0	170 – 230

Weld deposit data

Metal recovery approx. 140%.

Typical analysis % (All weld metal)

C	Si	Mn	Cr	Ni	Mo	N
0.03	0.8	0.7	22.5	9.5	3.0	0.15

Ferrite 30 FN WRC-92

Mechanical properties

	Typical values (IIW)	Min. values EN 1600
Yield strength $R_{p0.2}$	640 N/mm ²	450 N/mm ²
Tensile strength R_m	825 N/mm ²	550 N/mm ²
Elongation A_5	33 %	20 %
Impact strength KV		
+20°C	55 J	
-40°C	40 J	
Hardness approx.	240 Brinell	

Interpass temperature: Max. 150°C.

Heat input: 0.5 – 2.5 kJ/mm.

Heat treatment: Generally none (in special cases quench annealing at 1100 – 1150°C).

Structure: Austenite with approx. 30% ferrite.

Scaling temperature: Approx. 850°C (air).

Corrosion resistance: Very good resistance to pitting and stress corrosion cracking in chloride containing environments.

Approvals

–

Welding positions

Ø 4.0–5.0

