

TFW-410NiMo

JIS Z 3323 TS410NiMo-FC1
AWS A5.22 E410NiMoT1-1
EN 12073 T 13 4 P C 2

Characteristics and Applications:

TFW-410NiMo is a gas-shielded flux-cored wire with better control of hydrogen levels and excellent impact toughness at 0°C. It is generally used for welding of ASTM CA6NM castings, materials, with similar composition, and turbines of hydro plant.

Notes on Usage:

1. Use 99.8% or higher purity of CO₂ as shielding gas.
2. Pre-heat and inter-pass temperature 150°C~260°C, and post weld heat treatment.

Typical chemical composition (wt%) :

C	Si	P	S	Mo	Mn	Ni	Cr	Cu
0.040	0.28	0.015	0.008	0.45	0.27	4.50	11.30	0.01

Typical mechanical properties of weld metal :

TS (MPa)	EL %	CVN 0°C J	PWHT
875	19	46	610°C x 1hrs

Welding position



Sizes and recommended current range (DC <+>)

Diameter (mm)	1.2	
Welding condition	A	V
F、HF	130-220	24-33
H	140-180	25-29
V-UP	130-160	24-28
OH	150-180	25-29

*The information contained or otherwise referenced herein is presented only as "typical" without guarantee or warranty, and Tien Tai Electrode Co., Ltd. expressly disclaims any liability incurred from any reliance thereon. Typical data is obtained when welded and tested in accordance with AWS specification. Other tests and procedures may produce different results. No data is to be construed as recommendation for any welding condition or technique not controlled by Tien Tai Electrode Co., Ltd.