

TL-581

JIS Z 3212 D5016
AWS A5.1 E7018-1
EN499 E 42 4 B 3 2

Characteristics and Applications:

TL-581 is an iron powder type of low hydrogen electrode for all-position welding of 490N/mm² grade high tensile steel. It performed with higher deposition rate, good X-ray soundness, good mechanical properties and beautiful bead appearance. With excellent notch toughness at the temperature of -40°C to -50°C, it is very suitable for low alloy steels, medium carbon steels, heavy steel plates, cast steels and especially for welding of Aluminum Killed steel of LPG.

Notes on Usage:

1. Dry the electrodes at 300-350°C for 60 minutes and then keep at 100-150°C before using.
2. Use back-step method and hold for 3-5 seconds at every end-up to prevent arc starting from blowholes.
3. Maintaining short arc length as possible is highly recommended. While welding with weave method, moving range should be controlled within 3 times of the wire's dia.
4. Clean up the contaminations on the base metal.

Typical chemical composition of weld metal (wt%)

C	Mn	Si	P	S
0.08	1.30	0.5	0.02	0.008

Typical mechanical properties of weld metal

YS (MPa)	TS (MPa)	EL %	CVN -45°C J
500	580	30	98

Welding position



Sizes and recommended current range (AC or DC <+>)

Diameter (mm)		2.6	3.2	4.0	5.0
Length (mm)		350	350	450	450
Amps	F	55-85	90-130	130-180	170-240
	V&OH	50-80	90-120	110-160	150-180

*The information contained or otherwise referenced herein is presented only as "typical" without guarantee or warranty, and Tien Tai Electrode Co., Ltd. expressly disclaims any liability incurred from any reliance thereon. Typical data is obtained when welded and tested in accordance with AWS specification. Other tests and procedures may produce different results. No data is to be construed as recommendation for any welding condition or technique not controlled by Tien Tai Electrode Co., Ltd.