

TL-76A1

JIS Z 3223 DT1216
AWS A5.5 E7016-A1
EN1599 E Mo B 1 2

Characteristics and Applications:

TL-76A1 is a low hydrogen type electrode in which the normal chemical composition is 0.5Mo . It is for 490N/mm² high tensile steel available in all positions and suitable for welding of C-Mo steels used at about 500°C (e.g. ATPA12, A335-P1 of steel pipes, STBA12, A209-T1, A161-T1 of heat exchanger, A217-WCI casting steel, and A182-F1,A366-F1 of forging steels). Proper base metals are including structural steel, steel pipe for heat transfer, pressure vessel, alloy steel pipe, carbon steel for mechanical fabrication.

Notes on Usage:

1. Clean up the contaminations on the base metal and welding seam so as not to derogate the weld metal quality from particles.
2. Dry the electrodes at 350-400°C for 60 minutes before use.
3. Use back-step method and hold for 3-5 seconds at every end-up to prevent arc starting from blowholes.
4. Maintaining short arc length as possible is highly recommended. While welding with weave method, moving range should be controlled within 3 times of the wire's dia.
5. When the heat input is excessive, the impact value tends to be reduced. Therefore, select proper heat input depending on the required impact value.
6. Pre-heat the workpiece at 100~200°C and PWHT at 620~680°C.

Typical chemical composition of weld metal (wt%)

C	Mn	Si	P	S	Mo
0.07	0.50	0.50	0.015	0.010	0.45

Typical mechanical properties of weld metal

YS (MPa)	TS (MPa)	EL %	PWHT
480	560	30	620°Cx1hr

Welding position



Sizes and recommended current range (AC or DC <+>)

Diameter (mm)		3.2	4.0	5.0
Length (mm)		350	450	450
Amps	F	90-130	140-190	190-240
	V&OH	80-120	120-160	-

* The information contained or otherwise referenced herein is presented only as "typical" without guarantee or warranty, and Tien Tai Electrode Co., Ltd. expressly disclaims any liability incurred from any reliance thereon. Typical data is obtained when welded and tested in accordance with AWS specification. Other tests and procedures may produce different results. No data is to be construed as recommendation for any welding condition or technique not controlled by Tien Tai Electrode Co., Ltd.