



BLACSEN BS-1

Black Colorant

Packaging Unit Aerosol 420ml/can, 20cans/Box

:

Features

- With primary components like superparticle graphite and heat-resistant fluorine resin, this product creates smooth black coating with 2~3 μ m thick film.
- Film with excellent water-resistance, oil-resistance and heat resistance
- Powerful film.
- Excellent cohesion and antiabrasion.
- Excellent antirusting
- One touch spray and easy-to-use.
- Application to necessary place is possible.

Uses

Black coloring of steel, stainless, aluminum, copper and other metals

How to Use

- Degrease oil content, dirt and dust on the metal surface by using NABAKEM DC-5000.
- Shake the container before using it.
- Apply it 20~30cm away from target object and wait for tack free drying.
- Apply it again depending on desired thickness.
- Time for tack free drying is about 2~3 minutes.
- Complete hardening takes 24 hours.
- Use the target after complete hardening.
- Leave the target for one hour after spraying and harden it for 10~20 minutes at 150~200°C.
- Solvent resistance, cohesion and heat resistance increase.

Cautions

- Do not use it toward flame.
- Do not use it near heater or stove.

- Do not use it in the room where fire is used.
- Do not keep it in the place above 40°C.
- Provide ventilation after using it in the closed room.
- Do not throw it into fire.
- Make the hole in the container to remove residual gas after use
- Do not keep it in the closed place.
- Spraying may not work well at the temperature below 5°C.