

TFS-330

Basicity : 2.0

EN ISO 14174 S A AF 2 DC

Characteristics and Applications:

TFS-330 is designed for both butt and fillet welding applications. TFS-330 behaves neutrally with regard to carbon content in the filler wire. The metallurgical behavior of the flux in respect to silicon and manganese is also neutral and as a result there is minimal burn out or pick up of these elements. The resultant weld bead is free from slag residue and requires little or no post weld dressing. Grain size according to DIN EN 760 : 2-20.

- For submerged arc welding of the 300 series stainless steels, especially for 347 & 2209
- Applied to chemical plants, offshore, pressure vessels, storage tanks, power generation constructions, etc.

Notes on usage:

1. Flux exposed to atmosphere for an excess period must be re-baked at 300-350°C for 1~2hr holding time.

Typical chemical composition of weld metal (wt %) :

Wire	C	Mn	Si	P	S	Mo	Cr	Ni	Cu	Others
TW-347	0.04	1.82	0.58	0.03	0.01	0.10	19.0	10.2	0.12	Nb:0.70
TW-2209	0.02	1.20	0.56	0.02	0.01	2.82	21.8	9.0	0.07	N:0.15

Typical mechanical properties of weld metal:

Wire	Yield strength MPa(ksi)	Tensile strength MPa(ksi)	Elongation %	Charpy V-Notch J (ft-lbf)	Temperature °C(°F)
TW-347	460(67)	620(90)	36	50(37)	-110(-166)
TW-2209	591(86)	780(113)	31	74(55)	-40(-40)

* The information contained or otherwise referenced herein is presented only as "typical" without guarantee or warranty, and TienTai Electrode Co., Ltd. expressly disclaims any liability incurred from any reliance thereon. Typical data is obtained when welded and tested in accordance with AWS specification. Other tests and procedures may produce different results. No data is to be construed as recommendation for any welding condition or technique not controlled by TienTai Electrode Co., Ltd.