# SK A45-G

high-alloyed steels

**Classifications** 

gas-shielded metal-cored wire

DIN 8555

#### MF 10-GF-65-GT

#### **Characteristics**

Chromium-Niobium-Molybdenum alloy with addition of Tungsten and Vanadium designed to resist high stress grinding abrasion with low impact and solid erosion at service temperatures up to 650 °C. The deposits will readily show stress relief cracks.

Microstructure: Austenitic matrix with hexagonal primary and eutectic carbides and nodular Nb carbides with complex combined carbides

Machinability: Grinding only

Oxy-acetylene cutting: Cannot be flame cut

Deposit thickness: 8 to 12 mm in 2 or 3 layers

Shielding gas: Argon + 2 % Oxygen

### Field of use

Wear plates, sinter finger crushers, exhaust fan blades in pellet plants, perlite crushers, bucket teeth and lips on bucketwheel excavators, boiler fan blades, burden area in blast furnace bells, etc.

<b>Typical</b>	analy	vsis	in	%
Typiour	unun	y 010		/ u

С	Mn	Si	Cr	Мо	Nb	W	V	Fe
5.3	0.1	0.7	21.0	6.3	6.0	1.8	0.75	balance

## Typical mechanical properties

Hardness as welded: 63 HRC

Form of delivery and recommended welding parameters						
Wire diameter [mm]	Amperage [A]	Voltage [V]	Stick-out [mm]			
1.6	180 – 200	26 - 30	20 max.			

244