

Gas Metal Arc Welding

JIS Z3321 Y316LSi
 AWS A5.9 ER316LSi
 DIN 8556-SG 1.4430

MS M-316LSi Solid Wires for Stainless Steel

Applications Suitable for welding of extra-low carbon 18%Cr-12%Ni-2%Mo stainless steel. Usage as MS M-316L, but the 0.65-1.0% silicon content improves wetting behavior in the gas shielded welding process.

Brand Name		MS M-316LSi							
Representative of diameter (mm)	0.8	0.9	1.0	1.2	1.6	-	-	-	-
Chemical composition of wire (%)	C	Si	Mn	P	S	Ni	Cr	Mo	-
	≤ 0.030	0.65-1.00	1.0-2.5	≤ 0.03	≤ 0.03	11.0-14.0	18.0-20.0	2.0-3.0	-
Mechanical property of deposited metal									
Tensile strength	≥ 510 N/mm ²								
0.2% Offset strength	≥ 205 N/mm ²								
Elongation	≥ 35 %								
Impact test	2mm Vnotch Impact value at -196 °C 49 J								
Welding position	Horizontal/Flat position								
Welding polarity	DC-EP								
Shielding gas	98%Ar - 2%O ₂								
Welding current	Dia.0.8 mm	Dia.0.9 mm	Dia.1.0 mm	Dia.1.2 mm	Dia.1.6 mm				
	80-180A	120-200A	140-250A	170-300A	200-350A				
Packing	12.50 kgs standard other packing weight can be provided upon request.								