

Gas Tungsten Arc Welding

MS T-317L Filler Rod for Stainless Steel

Applications Suitable for welding of 317L stainless steel. Used same as MS T-317 and reduces the possibility of intergranular carbide precipitation and increases the resistance to intergranular corrosion.

Brand Name		MS T-317L							
Representative of diameter (mm)	1.0	1.2	1.6	2.0	2.4	2.6	3.2	4.0	5.0
Representative of length	1000 mm Standard or 950 mm Upon requested								
Chemical composition of wire (%)	C	Si	Mn	P	S	Ni	Cr	Mo	-
	≤ 0.030	≤ 0.65	1.0 - 2.5	≤ 0.03	≤ 0.03	13.0-15.0	18.5-20.5	3.0-4.0	-
Mechanical property of deposited metal									
Tensile strength	≥ 500 N/mm ²								
0.2% Offset strength	≥ 205 N/mm ²								
Elongation	≥ 30 %								
Impact test	NA								
Welding position	All position								
Welding polarity	DC-EN								
Shielding gas	Ar								
Welding current	Dia. 1.2 mm		Dia. 1.6 mm			Dia. 2.4 mm			
	30-80 A		40-120 A			50-150 A			
Packing									
Inner case weight (kg)	5.00								