UTP A Celsit 706 V		Tool steels
Classifications		TIG rod
EN 14700	DIN 8555	AWS A 5.21
R Z Co2	WSG 20-G0-40-CSTZ	ER CoCr-A

Characteristics and field of use

UTP A CELSIT 706 V is suitable for hardfacing of parts subject to a combination of erosion, corrosion, cavitation, pressure, impact, abrasion and high heat up to 900 °C, such as tight surfaces of fittings, valve seats and cones for combustion engines, gliding surfaces metal to metal, highly stressed hot working tools without thermal shock, milling, mixing and drilling tools.

Excellent gliding characteristics, very good polishability, high toughness, non-magnetic. Machinable by grinding and with tungsten carbide tools.

Hardness of pure weld deposit: 40 – 42 HRC Hardness at 500 °C: approx. 33 HRC

Typical analysis of rod and wire in %				
С	Cr	W	Co	
1.2	27.0	4.5	balance	

Welding instructions

Clean welding area, preheating temperature 450 – 600 °C, very slow cooling.

Form of delivery and recommended welding parameters				
Rod diameter x length [mm]	Current type	Shielding gas (EN ISO 14175)		
2.4 x 1000 mm*	DC (-)	11		
3.2 x 1000 mm	DC (-)	11		
4.0 x 1000 mm	DC (-)	11		
5.0 x 1000 mm	DC (-)	11		
Adjust acetylene excess (reducing flame) in oxyacetylene welding.				
* Available on demand.				