

UTP A 80 Ni		nickel alloys					
Classifications		solid wire					
EN ISO 18274	AWS A5.14	Material-No.					
S Ni 2061 (NiTi3)	ER Ni-1	2.4155					
Characteristics and field of use							
<p>UTP A 80 Ni is suited for joining and surfacing on commercial pure nickel grades, including LC nickel, nickel alloys and nickel-clad steels.</p> <p>Such materials are employed primarily in the construction of pressure vessels and apparatus in the chemical industry, in the food industry and for power generation, where good behaviour under corrosion and temperature is demanded.</p> <p>The weld metal has an excellent resistance in a lot of corrosive medias, from acid to alkali solutions.</p>							
Typical analysis in %							
C	Si	Mn	Ni	Ti	Fe		
< 0.02	< 0.3	0.3	balance	3.3	< 0.1		
Mechanical properties of the weld metal							
<i>Yield strength $R_{p0.2}$</i>		<i>Tensile strength R_m</i>		<i>Elongation A</i>		<i>Impact strength K_V</i>	
MPa		MPa		%		J (RT)	
> 300		> 450		> 30		> 160	
Welding instructions							
Clean the weld area thoroughly to avoid porosity. Groove angle about 70 °. To be welded by stringer bead technique.							
Approvals							
TÜV (No. 00950), ABS							
Form of delivery and recommended welding parameters							
<i>Wire diameter [mm]</i>	<i>Current type</i>		<i>Shielding gas (EN ISO 14175)</i>				
0.8	DC (+)		I 1	I 3	Z-ArHe-HC-30 / 2 / 0.05		
1.0	DC (+)		I 1	I 3	Z-ArHe-HC-30 / 2 / 0.05		
1.2	DC (+)		I 1	I 3	Z-ArHe-HC-30 / 2 / 0.05		